

Goodspeed *FUN 40*

(Formerly known as PORPLASTIC FUN 40)

Elastic and decorative surfaces for playgrounds,
critical fall height 1.14m

PLAYGROUNDS FOR ALL

Application Fields

Playgrounds Play zones in school

Walkways in kindergartens or schools

Toddler zones in open air baths

Coating of concrete green bodies



Critical fall height
= 1.14m



Hygienic



Creative use of colours

Performance check



Hygienic



Easy to clean with
high pressure
stream heater



UV sealer
recommended for
sensitive colour



Jointless



Total Thickness
40 – 45 mm



Critical Fall Height
1.14 m



Permanent Elasticity



Water-permeable



Available in many
colours



Weather-resistant




Tested
according DIN
1177:2018



Layer	Consumption	Thickness	Application
WEARING LAYER Goodspeed T760/T770/T776 Goodspeed EPDM (1-4mm) 	2 – 3 kg/m ² 10 – 15 kg/m ²	ca. 10 – 15 mm	Manual or paving machine
HIGHLY ELASTIC LAYER Goodspeed T770/T776 Goodspeed SBR (2-8mm) 	ca. 1.8 kg/m ² ca. 18 – 20 kg/m ²	ca. 30 mm	Manual or paving machine
PRIMER Goodspeed P270 (for asphalt) 	ca. 0.15 – 0.20 kg/m ²	ca. 0.10 mm	Roll or Spray
PRIMER Goodspeed P274 (for concrete) 	0.10 – 0.20 kg/m ²	ca. 0.10 mm	Roll or Spray

Remark: for further information please refer to the product data sheets or contact our technical service. All data are approximate values. Therefore, no liability claims can be derived from the system data sheet. As all Goodspeed data sheets are updated on a regular basis it is the users' responsibility to obtain the most recent issue (see www.porplastic.com or contact us directly). Date of issue: June 2025 – all technical information is subject to change without prior notice.



Distributor:

Goodspeed America Inc., 24624 Interstate 45 North, Suite 200 • Spring, Texas 77386, U.S.A.
Email: bstorey@goodspeed-america.com, www.goodspeed-america.com

