

**Goodspeed C523***(Formerly known as PORPLASTIC C523)***Technical Data Sheet****INDOOR/OUTDOOR**

Product 02252300

SELF LEVELLING LAYER for sports surfaces, 2 comp. PU

1 General Data

Application Fields

Goodspeed C523 is used for elastic sports surfaces as self-levelling layer for durable and resistant indoor sports floorings and outdoor multilayer systems. Typical uses for these systems are point- or small-area elastic floorings for sports halls and outdoor systems.

Goodspeed C523 is also frequently used for the renovation and renewing of existing indoor PU sports surfaces (re-topping).

Product Description

Goodspeed C523 is a pigmented and solvent free, two component PUR self levelling layer with good and lasting elastic properties, durability and wear resistance.

Due to its long pot life Goodspeed C523 is easy to apply, it shows excellent curing behaviour and good values of final strength. Goodspeed C523 has to be sealed to achieve increased UV- and colour stability.

Sports Surfacing Systems

Point-elastic, mixed elastic or combined elastic Goodspeed **INDOOR/OUTDOOR** PUR-systems

Goodspeed **multilayer** systems

Goodspeed **TENNIS** systems

Re-topping of old PUR-systems

Technical Support

For detailed descriptions of Goodspeed systems see Goodspeed system data sheets or contact our technical support.

Phone: +49 174 310 2273

E-Mail: info@porplastic.de

(A) Technical Data

Mixture (A+B)

1. Density (23°C) (DIN 53217)	ca. 1.28 g/cm ³
2. Viscosity	ca. 1 400 mPas
3. Shore A hardness (23°C/50% rel. humidity) after 24 h	ca. 57
after 28 days	ca. 75
4. Packaging size	Comp. A: 24 kg Comp. B: 6 kg
5. Mixing ratio A : B (parts by weight)	100 : 25
6. Colour	on request
7. Shelf life / Storage	12 months at 10–25°C
8. Permissible relative humidity	min. 30% - max. 80%
9. Substrate and application temperature	10-30°C (min. 3°C above dew point)
10. Processing time (23°C)	ca. 25 minutes
11. Can be walked on (depending on circumstances)	after 12-24 hours
12. Material consumption per layer	2.0 – 3.0 kg/m ²
13. Tensile strength (DIN 53504)	4.8 N/mm ²
14. Elongation at break (DIN 53504)	ca. 80 %
15. Tear strength (DIN 53515)	ca. 12 N/mm ²

Distributor: Goodspeed America Inc., 24624 Interstate 45 North, Suite 200 • Spring, Texas 77386, U.S.A.,
bstorey@goodspeed-america.com | www.goodspeed-america.com

Manufacturer: PORPLASTIC Sportbau von Cramm GmbH, Dieselstr. 14 96450 Coburg, Germany, tel. +49 174 310 2273 |
info@porplastic.de | www.porplastic.com



Goodspeed C523

Technical Data Sheet

INDOOR/OUTDOOR

(Formerly known as PORPLASTIC C523)

Product 02252300

SELF LEVELLING LAYER for sports surfaces, 2 comp. PU

2 Processing Instructions

Substrate Preparation

Goodspeed C523 is usually applied on pre-fabricated or in situ rubber granule mats sealed with Goodspeed L375, PUR foam mats or other PU-coatings. In case of coatings or pore sealer older than 3 days, grinding of the surface is necessary. The application of Goodspeed C523 should best be realized 4 – 6 hours after the previous layer (at least within 24 hours). We recommend ap-pling an scratch layer of Goodspeed C523 (consumption ca. 0.5 kg/m²) to fill the elastic layer completely and eliminate the possibility of bubbles in the coating. Substrates to be coated have to be dry, load bearing, clean and free of loose particles and contaminants such as oils, fats, greases, paint residues, chemicals, algae and laitance. For application on other substrates such as wood, test have to be performed to find the right primer. In case of application to concrete, FLOORFINDER EP-P210 has to be used as a primer.

Re-topping:

Please contact our technical support before re-topping old PUR surfaces.

Adhesion tests should be carried out and they will determine the substrate preparation. It may be necessary to grind, remove the dust and apply a primer before the installation of Goodspeed C523. In all cases the surface must be thoroughly cleaned and left to dry completely. Then the primer is applied onto the pre-treated substrate.

Processing

Goodspeed C523 is supplied in the correct proportions of component A and B. The optimal processing temperature is between 15 – 25°C. Component A has to be homogenized before application. For application pour component A and B into a mixing container in the right mixing ratio. Use a slow rotating mixer rotating at approximately 300 - 500 rev/min for at least 3 -4 minutes until the blend is homogeneous and streak free.

Ensure that the mixer reaches the sides and bottom areas of the mixing vessel. Pour the mix into another clean container and mix it again for one additional minute.

The well mixed material is applied on the pre-treated substrate with a squeegee or best a notched trowel (selection of tooth size determines the thickness of the layer).

We recommend to roll the still liquid coating with a metal spiked roller (e. g. Multitool) to ensure optimal defoaming. It is recommended to wear spiked shoes for this operation which enable the applicator to walk in the

freshly applied coating. After the application the material should not be treated with water for 24 hours. At low temperatures and humidity, the speed of reaction is reduced resulting in a longer pot life, re-coating interval and open time. The speed of reaction is accelerated at high temperatures and humidity and the converse is true.

Cleaning

Tools should be cleaned using Goodspeed SO-X12. Never use water or alcoholic solvents as cleaners!

Safety Instructions

For health and safety protection, transport regulations and waste management please consider the Material Safety Data Sheet. Users are advised to wear gloves and eye protection when mixing or applying Goodspeed C523. Goodspeed C523 is non hazardous in its cured condition. The product meets the requirements of the EC directive 2004/42/EC for VOC content.

CE-Mark

CE-Mark according to EN 14904

Details see CE-conformity mark and conformity declaration.



Disclaimer

All information in this technical data sheet is based on our current knowledge and experience. This does not release the applicator from performing their own tests as many application factors, beyond our control, affect the application of our product. No guarantee of characteristics or suitability for a special purpose can be derived from this information. All present data, descriptions, drawings, photos, ratios, weights etc. are subject to change without prior notice and do not represent contracted characteristics of the product.

Due to different materials, sub-bases and working conditions, no guarantee of an application result or any liability claims can be derived from these details or from an unwritten technical advice except for liability claims based on:

-damage to life, body or health resulting from a negligent violation of obligations or a deliberate or negligent violation of obligation of a legal representative or assistant and

-if we are charged with intention or gross negligence.
The user has to test the products for their intended use. The user is responsible for following existing laws and orders and for observing third party trade mark rights.

As all Goodspeed data sheets are updated on a regular basis it is the users responsibility to obtain the most recent issue (see www.porplastic.com or contact us directly).

Distributor: Goodspeed America Inc., 24624 Interstate 45 North, Suite 200 • Spring, Texas 77386, U.S.A.,
bstorey@goodspeed-america.com | www.goodspeed-america.com

Manufacturer: PORPLASTIC Sportbau von Cramm GmbH, Dieselstr. 14 96450 Coburg, Germany, tel. +49 174 310 2273 |
info@porplastic.de | www.porplastic.com