

**Product 01438000** 3-comp. EP advanced resin scratch/levelling/grouting coat, water based

## 1 General Data

### Fields of application

FLOORFINDER EP-L380 is designed for use as a scratch / coat to seal pores, voids and imperfections on concrete surface before applying FLOORFINDER systems. It is also recommended for use as a levelling compound to improve the evenness of the floor for a better surface finish for the topping.

### Product description

FLOORFINDER EP-L380 is a three-component, advanced resin-based compound with unique rheological properties. It has a thick and yet fluid consistency which makes it a versatile product ideal for sub-base preparation use for its filling, sealing and levelling capabilities.

### Characteristics

- High solids and higher DFT
- Advanced resin system
- Low VOC emission
- High water vapour permeability
- Good adhesion to substrate
- Low / no odour
- Solvent free
- Self-levelling

### FLOORFINDER systems

FLOORFINDER EP-L380 is a scratch / seal coat for concrete surface and a laminating base coat for water-based FLOORFINDER waterproofing systems.

FLOORFINDER **PERM DECK**

<b>(A) Technical data</b>	
<b>Liquid mixture (A+B+C)</b>	
1. Solids content	83 %
2. Density (25°C)	1.84 g/cm <sup>3</sup>
3. Viscosity (25°C)	2000–4000 mPas
4. Packaging size	27 kg (20.1 kg A + 2.4 kg B + 4.5 kg C)
5. Colours	Grey 1, Grey 2, White, Green, Red and Blue
6. Shelf life	12 months in closed original container
7. Storage	Dry and frost-free at 10–30°C, avoid direct sunlight

<b>(B) Technical data</b>	
<b>Cured material</b>	
1. Adhesive strength (DIN ISO 4624)	> 1.5 N/mm <sup>2</sup> (concrete failure)

### Care and maintenance

The lifespan & performance of your waterproofing system can be extended considerably by adopting a regular cleaning and care programme

### Technical support

For system build up possibilities and detailed information relating to the laying of FLOORFINDER products, please refer to the FLOORFINDER System Planner or contact Floorfinder Asia Sdn Bhd directly.

Tel: +603 3290 7644  
e-mail: [info@floorfinderasia.com](mailto:info@floorfinderasia.com)

#### Distributor:

Goodspeed America Inc., 24624 Interstate 45 North, Suite 200 • Spring, Texas 77386, U.S.A.,  
email: [bstorey@goodspeed-america.com](mailto:bstorey@goodspeed-america.com), [www.goodspeed-america.com](http://www.goodspeed-america.com)

#### Manufacturer:

Floorfinder Asia Sdn. Bhd., No. 28, Lorong Sungai Puloh 1A/KU6, Jalan Sungai Puloh, Batu 5 3/4, Kapar, 42100 Klang, Selangor Darul Ehsan, Malaysia, tel: +603 3290 7644, email: [info@floorfinderasia.com](mailto:info@floorfinderasia.com), [www.floorfinderasia.com](http://www.floorfinderasia.com) – A division of VIACOR VISION AG, SWITZERLAND

**Product 01438000** 3-comp. EP advanced resin scratch/levelling/grouting coat, water based

## 2 Application method

### Substrate preparation

The substrate must be firm, clean, dry and have a pull-off strength of 1.5 N/mm<sup>2</sup> minimum.

The product can be used on green concrete.

Repair imperfections (holes and cracks) with an epoxy patching compound such as FLOORFINDER EP-T703 where necessary.

Remove surface laitance, contaminants, coating, curing compound and all weak and loose materials.

Prepare substrate by Captive Shot Blasting or Diamond Grinding to provide the appropriate surface profile for optimum mechanical interlocking.

### Application

#### Priming

Apply FLOORFINDER EP-P285 Primer at the consumption rate of min. 0.2 kg/m<sup>2</sup> by roller.

Allow to cure for a minimum of 8 hours but not longer than 24 hours before the application of FLOORFINDER EP-L380.

#### Applying FLOORFINDER EP-L380

Before starting the application, the material temperature must be close to site conditions.

Mix component A for 2 minutes.

Add component C into component A and mix for 2-3 minutes. Mix with a suitable mixer at a speed of 500 rpm to avoid incorporating excessive air into the mix.

Empty contents of component B (Hardener) into mixture and mix for 2 minutes.

Transfer the mixture into another clean container and mix for 1 minute.

#### As scratch Coat

Spread the mixed product onto the surface with a trowel.

Press/scratch hard against the surface to push the material to fill and seal the surface.

If a smooth finish is required, it is recommended to carry out a light sanding of the surface before proceeding to apply the top coat.

### (C) Technical data

#### Liquid mixture (A+B+C)

1.	Mixing ratio A : B : C	100 : 11.9 : 22.4 by weight (kg)
2.	Working time	approx. 25 min. (25°C) approx. 20 min. (30°C)
3.	Application temperature	10 – 30°C (min. 3°C above dew point)
4.	Material consumption scratch coat thick layer coating	0.8 – 1.2 kg/m <sup>2</sup> 2.5 – 3.0 kg/m <sup>2</sup>
5.	Following coating (25°C)	within 24 hours
6.	Cure time to withstand: Foot traffic (25 °C) Heavy Traffic (25°C) Exposure to water immersion (25°C)	after 6 - 8 hours after 3 days after 7 days

#### As a Levelling Layer

Apply FLOORFINDER EP-L380 at the consumption rate of 2.5-3.0 kg/m<sup>2</sup> minimum using a pin rake or notch trowel. If necessary, it can be diluted with water to the maximum of 2% by weight to facilitate a better flow.

Do not apply thicker than 2 mm. Provide good ventilation to ensure that the relative air humidity does not exceed 75% during application and curing as it will inhibit evaporation of water and affect cure.

For cleaning of tools and other contaminations use water.

### Overcoating

The second coat can be applied within 24 hrs without grinding. If longer, the surface has to be grinded before overcoating.

#### Distributor:

Goodspeed America Inc., 24624 Interstate 45 North, Suite 200 • Spring, Texas 77386, U.S.A.,  
email: [bstorey@goodspeed-america.com](mailto:bstorey@goodspeed-america.com), [www.goodspeed-america.com](http://www.goodspeed-america.com)

#### Manufacturer:

Floorfinder Asia Sdn. Bhd., No. 28, Lorong Sungai Puloh 1A/KU6, Jalan Sungai Puloh, Batu 5 3/4, Kapar, 42100 Klang, Selangor Darul Ehsan, Malaysia, tel: +603 3290 7644, email: [info@floorfinderasia.com](mailto:info@floorfinderasia.com), [www.floorfinderasia.com](http://www.floorfinderasia.com) – A division of VIACOR VISION AG, SWITZERLAND

**Product 01438000** 3-comp. EP advanced resin scratch/levelling/grouting coat, water based

### 3 Further information

#### CE-Mark



#### CE-Mark according to EN 13813

EN 13813: 2003-01, Screed material and floor screeds - Screed materials - Properties and requirements is the basis for requirements for floor screeds used in indoor flooring constructions. Resin coatings and sealer are also subject to this norm.

Details see CE-conformity mark and conformity declaration.

#### Warnings and precautions

Information relating to the safe handling of this product can be found in the Material Safety Data Sheet. Local regulations concerning the safe handling of epoxy resin based coating materials must be observed.

Suitable protective clothing including suitable eye protection must be worn.

#### Disclaimer

All information in this technical data sheet is based on our current knowledge and experience. This does not release the applicator from performing their own tests as many application factors, beyond our control, affect the application of our product. No guarantee of characteristics or suitability for a special purpose can be derived from this information. All present data, descriptions, drawings, photos, ratios, weights etc. are subject to change without prior notice and do not represent contracted characteristics of the product.

Due to different materials, sub-bases and working conditions, no guarantee of an application result or any liability claims can be derived from these details or from an unwritten technical advice except for liability claims based on:

- damage to life, body or health resulting from a negligent violation of obligations or a deliberate or negligent violation of obligation of a legal representative or assistant and
- if we are charged with intention or gross negligence.

The user has to test the products for their intended use. The user is responsible for following existing laws and orders and for observing third party trade mark rights.

As all Floorfinder data sheets are updated on a regular basis it is the users responsibility to obtain the most recent issue (see [www.floorfinderasia.com](http://www.floorfinderasia.com)).

#### Distributor:

Goodspeed America Inc., 24624 Interstate 45 North, Suite 200 • Spring, Texas 77386, U.S.A.,  
email: [bstorey@goodspeed-america.com](mailto:bstorey@goodspeed-america.com), [www.goodspeed-america.com](http://www.goodspeed-america.com)

#### Manufacturer:

Floorfinder Asia Sdn. Bhd., No. 28, Lorong Sungai Puloh 1A/KU6, Jalan Sungai Puloh, Batu 5 3/4, Kapar, 42100 Klang, Selangor Darul Ehsan, Malaysia, tel: +603 3290 7644, email: [info@floorfinderasia.com](mailto:info@floorfinderasia.com), [www.floorfinderasia.com](http://www.floorfinderasia.com) – A division of VIACOR VISION AG, SWITZERLAND