

Product 01360000

2-comp.-EP base coat for FLOORFINDER **DESIGN QCV**,
coloured, low emission

1 General data

Fields of application

FLOORFINDER EP-Q3600 is used as base coat for FLOORFINDER **DESIGN** industrial floorings made with coloured quartz sand. The FLOORFINDER **DESIGN** floorings are characterized by their exceptional appearance and design properties.

Applications include public buildings, hospitals, schools, retail spaces and supermarkets, production halls especially in the food and beverage industry, laboratories, wine cellars and wholesale markets.

Product description

FLOORFINDER EP-Q3600 is a slightly coloured, ready to use, low emission 2-component epoxy base coat. The colour of the product has to match the colour of the quartz sand.

The construction product is tested according to the DIBT emission principles and meet the AgBB requirements.

In general, epoxy resins are not colour stable if exposed to UV light or under influence of weathering. We recommend to apply a colour stable sealer.

FLOORFINDER Systems

FLOORFINDER EP-Q3600 is the base coat in the FLOORFINDER Systems:
FLOORFINDER **DESIGN QCV**

Technical support

For system build up possibilities and detailed information relating to the laying of FLOORFINDER products, please refer to the FLOORFINDER System Planner or contact Floorfinder Asia Sdn Bhd directly.

Tel: +603 3290 7644

e-mail: info@floorfinderasia.com

(A) Technical data

Mixture (A+B)

1. Solids content	> 99 %
2. Density (20°C)	1.1 g/cm ³
3. Viscosity (20°C)	400 – 800 mPas
4. Pack size (2-Component pack)	28.6 kg (20 kg A + 8.6 kg B)
5. Colour	White, light grey, dark grey, blue, green, red
6. Shelf-life (20 °C)	12 months in originally closed container
7. Storage	Dry and frost free at 10 – 25°C, avoid exposure to direct sunlight

(B) Technical data

Cured material

1. Pull off strength (DIN EN ISO 4624)	> 1.5 N/mm ²
2. Shore-D-Hardness (DIN EN ISO 868)	74

Distributor:

Goodspeed America Inc., 24624 Interstate 45 North, Suite 200 • Spring, Texas 77386, U.S.A.,
email: bstorey@goodspeed-america.com | www.goodspeed-america.com

Manufacturer:

Floorfinder Asia Sdn. Bhd., No. 28, Lorong Sungai Puloh 1A/KU6, Jalan Sungai Puloh, Batu 5 3/4, Kapar, 42100 Klang, Selangor Darul Ehsan, Malaysia,
tel: +603 3290 7644, email: info@floorfinderasia.com, www.floorfinderasia.com – A division of VIACOR VISION AG, SWITZERLAND

Product 01360000

2-comp.-EP base coat for FLOORFINDER **DESIGN QCV**,
coloured, low emission

2 Application method

For detailed information concerning the application of FLOORFINDER **DESIGN** products please refer to the FLOORFINDER **DESIGN** application guide.

Substrate preparation

FLOORFINDER EP-Q3600 is applied directly onto a levelling layer made from FLOORFINDER EP-N1300 /S. The levelling layer must be clean and free of any substances which may impair adhesion.

Application

The Part A should be stirred for min. 1 – 2 minutes after which the entire contents of the Part B are added before mixing for min. 2 – 3 minutes with a suitable electrically driven stirrer. The stirrer should be kept submerged in the liquid to avoid the mixing in of air. The mixture should then be emptied into a clean container and mixed for a further minute. We recommend the application by equal batch numbers. The product is filled with FLOORFINDER QNV quartz sand. For partial mixtures, component A must be stirred well before the partial withdrawal.

FLOORFINDER EP-Q3600 is poured in portions onto the surface and spread with a spatula, flattening knife or trowel. Trowel lines and the formation of puddles must be avoided. After waiting for 10 – 15 minutes, the whole area is sprinkled with FLOORFINDER QCV coloured quartz sand. See FLOORFINDER **DESIGN** application guide.

Use FLOORFINDER SO-X10 to clean tools and contaminated areas.

Overcoating

See FLOORFINDER **DESIGN** application guide.

(C) Technical data

Mixture (A+B)

1. Mixing ratio A : B	100 : 43 by weight
2. Working time (20 °C)	approx. 20 – 25 minutes
3. Application temperature	10 – 30 °C (min. 3 K above the dew point)
4. Consumption (per coat)	approx. 600 g/m ²
5. Foot traffic (20°C)	after approx. 12 – 15 h
6. Full cure (20°C) mechanical stress chemical stress	7 d 28 d

Distributor:

Goodspeed America Inc., 24624 Interstate 45 North, Suite 200 • Spring, Texas 77386, U.S.A.,
email: bstorey@goodspeed-america.com | www.goodspeed-america.com

Manufacturer:

Floorfinder Asia Sdn. Bhd., No. 28, Lorong Sungai Puloh 1A/KU6, Jalan Sungai Puloh, Batu 5 3/4, Kapar, 42100 Klang, Selangor Darul Ehsan, Malaysia,
tel: +603 3290 7644, email: info@floorfinderasia.com, www.floorfinderasia.com – A division of VIACOR VISION AG, SWITZERLAND

Product 01360000

2-comp.-EP base coat for FLOORFINDER **DESIGN QCV**,
coloured, low emission

3 Further information

CE-Mark



CE-Mark according to DIN EN 13813

EN 13813 "Screed material and floor screeds – properties and requirements" specifies requirements for screed material for use in floor construction internally. Resin flooring and sealer coats are also covered by this standard. For details see CE mark and Declaration of Conformity

Decopaint-Guidelines (EU 2004/42/EG)

The maximum allowable VOC content for Product Category IIA j Type Lb products (in the ready to use state) is:

Stage II (from 2010) < 500 g/l VOC

In the ready to use state, this product contains less than 500 g/l VOC.

Warnings and precautions

Information relating to the safe handling of this product can be found in the Material Safety Data Sheet. Local regulations concerning the safe handling of epoxy resin-based coating materials must be observed.

Suitable protective clothing including suitable eye protection must be worn.

Disclaimer

All information in this technical data sheet is based on our current knowledge and experience. This does not release the applicator from performing their own tests as many application factors, beyond our control, affect the application of our product. No guarantee of characteristics or suitability for a special purpose can be derived from this information. All present data, descriptions, drawings, photos, ratios, weights etc. are subject to change without prior notice and do not represent contracted characteristics of the product.

Due to different materials, sub-bases and working conditions, no guarantee of an application result or any liability claims can be derived from these details or from an unwritten technical advice except for liability claims based on:

-damage to life, body or health resulting from a negligent violation of obligations or a deliberate or negligent violation of obligation of a legal representative or assistant and
-if we are charged with intention or gross negligence.

The user has to test the products for their intended use. The user is responsible for following existing laws and orders and for observing third party trademark rights.

As all FLOORFINDER data sheets are updated on a regular basis it is the user's responsibility to obtain the most recent issue (see www.floorfinderasia.com).

Distributor:

Goodspeed America Inc., 24624 Interstate 45 North, Suite 200 • Spring, Texas 77386, U.S.A.,
email: bstorey@goodspeed-america.com | www.goodspeed-america.com

Manufacturer:

Floorfinder Asia Sdn. Bhd., No. 28, Lorong Sungai Puloh 1A/KU6, Jalan Sungai Puloh, Batu 5 3/4, Kapar, 42100 Klang, Selangor Darul Ehsan, Malaysia,
tel: +603 3290 7644, email: info@floorfinderasia.com, www.floorfinderasia.com – A division of VIACOR VISION AG, SWITZERLAND