

Product 02025001 2-comp. PU primer for EP and PU, solvent free, transparent

1 General Data

Fields of application

FLOORFINDER PU-P2250 is a solvent free primer used as bonding agent on FLOORFINDER spray coatings and between sanded EP- or PU-substrates and subsequent layers for better adhesion.

Product description

FLOORFINDER PU-P2250 is a low viscosity, transparent, solvent-free 2 component primer.

FLOORFINDER PU-P2250 has outstanding bonding properties on non-absorbent substrates and membranes. The product is fast-curing, has a lot time range for overcoating and is easy to apply.

Technical support

For system build up possibilities and detailed information relating to the laying of FLOORFINDER products, please refer to the FLOORFINDER System Planner or contact Floorfinder Asia Sdn. Bhd. directly.

Tel: +603 3290 7644

e-mail: info@floorfinderasia.com

(A) Technical Data

Liquid

1. Density (20°C)	approx. 1.08 g/cm ³
2. Solids content	> 99 % by volume
3. Viscosity (20°C)	600 – 800 mPas
4. Packaging size	12.0 kg (7.5 kg A / 4.5 kg B)
4. Colour	transparent
5. Shelf life	12 months in closed original container
6. Storage	Dry at 15-25°C, avoid direct sunlight

Distributor:

Goodspeed America Inc., 24624 Interstate 45 North, Suite 200 • Spring, Texas 77386, U.S.A.,
email: bstorev@goodspeed-america.com | www.goodspeed-america.com

Manufacturer:

Floorfinder Asia Sdn. Bhd., No. 28, Lorong Sungai Puloh 1A/KU6, Jalan Sungai Puloh, Batu 5 3/4, Kapar, 42100 Klang, Selangor Darul Ehsan, Malaysia,
tel: +603 3290 7644, email: info@floorfinderasia.com, www.floorfinderasia.com – A division of VIACOR VISION AG, SWITZERLAND

Product 02025001 2-comp. PU primer for EP and PU, solvent free, transparent

2 Application method

Please refer also to our general application guideline.

Substrate Preparation

The substrate must be load-bearing as well as clean and free of dust and loose particles. All traces of contaminants such as oils, fats, greases, paint residues, chemicals, algae and laitance should be removed.

Membranes older than 2 weeks must be ground and cleaned before applying the primer.

Application

FLOORFINDER PU-P2250 is delivered in 2 component containers in the right mixing ratio. The A-component must be stirred for at least 1–2 minutes. Then the entire content of the B-component is emptied into the A-component container and the two components are mixed until homogeneous using a suitable electric stirrer (for at least 2 – 3 minutes). Processing temperature should be between 15 – 25°C.

FLOORFINDER PU-P2250 is applied onto the pre-treated substrate by roller or brush or spraying. Avoid puddles and apply a thin and uniform layer with 80 – 100 g/m² material consumption. Exceeding this rate can cause foaming and a very slow curing of the material.

At low temperatures and humidity, the speed of reaction is reduced resulting in a longer pot life, re-coating interval and open time. The speed of reaction is accelerated at high temperatures and humidity and the converse is true. Direct sunshine shortens the time frames considerably.

After application, the primer has to be protected from direct contact with water in order to avoid inter-coat adhesion problems.

For cleaning of tools and other dirt FLOORFINDER SO-X12 cleaner is recommended.

Overcoating

The next layer should be applied after 1 – 24 hours, when the solvents have evaporated.

(B) Technical Data

Liquid

1. Mixing ratio	100 : 60
2. Material consumption (depending on substrate)	80 – 100 g/m ²
3. Material temperature during application	15 – 25 °C
4. Application temperature	10 – 35°C (min. 3 K above dew point)
5. Pot life	max. 30 min (at 15°C) max. 15 min (at 25°C)
6. Relative humidity	min. 40% - max 85%
7. Overcoating at 25°C	after 4 – 24 hours

Distributor:

Goodspeed America Inc., 24624 Interstate 45 North, Suite 200 • Spring, Texas 77386, U.S.A.,
email: bstorev@goodspeed-america.com | www.goodspeed-america.com

Manufacturer:

Floorfinder Asia Sdn. Bhd., No. 28, Lorong Sungai Puloh 1A/KU6, Jalan Sungai Puloh, Batu 5 3/4, Kapar, 42100 Klang, Selangor Darul Ehsan, Malaysia,
tel: +603 3290 7644, email: info@floorfinderasia.com, www.floorfinderasia.com. – A division of VIACOR VISION AG, SWITZERLAND

Product 02025001 2-comp. PU primer for EP and PU, solvent free, transparent

3 Further information

CE-Mark



CE-Mark according to EN 13813

EN 13813: 2003-01, Screed material and floor screeds - Screed materials - Properties and requirements is the basis for requirements for floor screeds used in indoor flooring constructions. Resin coatings and sealer are also subject to this norm.

Details see CE-conformity mark and conformity declaration.

Decopaint-Guidelines (EU 2004/42/EG)

The maximum allowable VOC content for Product Category IIA j Type Lb products (in the ready to use state) is:

Stage II (from 2010) < 500 g/l VOC

In the ready to use state, this product contains less than 500 g/l VOC.

Warnings and precautions

Information relating to the safe handling of this product can be found in the Material Safety Data Sheet. Local regulations concerning the safe handling of epoxy resin based coating materials must be observed.

Suitable protective clothing including suitable eye protection must be worn.

Disclaimer

All information in this technical data sheet is based on our current knowledge and experience. This does not release the applicator from performing their own tests as many application factors, beyond our control, affect the application of our product. No guarantee of characteristics or suitability for a special purpose can be derived from this information. All present data, descriptions, drawings, photos, ratios, weights etc. are subject to change without prior notice and do not represent contracted characteristics of the product.

Due to different materials, sub-bases and working conditions, no guarantee of an application result or any liability claims can be derived from these details or from an unwritten technical advice except for liability claims based on:

- damage to life, body or health resulting from a negligent violation of obligations or a deliberate or negligent violation of obligation of a legal representative or assistant and
- if we are charged with intention or gross negligence.

The user has to test the products for their intended use. The user is responsible for following existing laws and orders and for observing third party trademark rights.

As all FLOORFINDER data sheets are updated on a regular basis it is the users responsibility to obtain the most recent issue (see www.floorfinderasia.com).

Distributor:

Goodspeed America Inc., 24624 Interstate 45 North, Suite 200 • Spring, Texas 77386, U.S.A.,
email: bstorey@goodspeed-america.com | www.goodspeed-america.com

Manufacturer:

Floorfinder Asia Sdn. Bhd., No. 28, Lorong Sungai Puloh 1A/KU6, Jalan Sungai Puloh, Batu 5 3/4, Kapar, 42100 Klang, Selangor Darul Ehsan, Malaysia,
tel: +603 3290 7644, email: info@floorfinderasia.com, www.floorfinderasia.com. – A division of VIACOR VISION AG, SWITZERLAND