

Product 02452300 2-comp. PU top coating, soft elastic, low emission, colored

1 General Data

Fields of application

FLOORFINDER PU-C523 is used indoors for soft elastic, sound absorbing surfaces as self-levelling coating. Typical uses for this high-quality product are residential homes for the elderly, kindergartens, schools, clinics, social rooms, offices and in general industrial floorings.

Product description

FLOORFINDER PU-C523 is a pigmented, low emission and solvent free, soft elastic two-component PU self levelling coating. FLOORFINDER PU-C523 has outstanding mechanical properties and is permanently elastic. It fulfils the requirements of German AgBB, the standard for low emission in construction products. Due to its long pot life FLOORFINDER PU-C523 is easy to apply and shows a good curing behaviour. In general, aromatic polyurethane resins are not colour stable if exposed to UV light or under influence of weathering. We recommend to apply a colour stable PU sealer.

FLOORFINDER systems

FLOORFINDER PU-C523 is the elastic coating for the FLOORFINDER systems:

FLOORFINDER **ELASTIC**
FLOORFINDER **ELASTIC deco**

Characteristics

- Sound absorbing, warm to foot
- Static crack-bridging
- Soft elastic
- Low odour

(A) Technical data

Liquid component

1. Solids content	99 %
2. Density (25°C)	1.4 g/cm ³ (Mixed)
3. Viscosity (28°C)	3000 - 4000 cps
4. Packaging size	30 kg (A+B 25: 5 kg)
5. Colours	Pigmented
6. Shelf life	9 months in closed original container
7. storage	Dry at 10–30°C, avoid direct sunlight

(B) Technical data

Cured material

1. Adhesive strength (DIN EN ISO 4624)	>2.0 N/mm ² (concrete failure)
2. Hardness Shore A (DIN EN ISO 868)	Shore D35 after 7 days Shore A85-87 after 7 days
3. Elongation at break (DIN 53504)	>170%
4. Tensile strength (DIN 53504)	>7 N/mm ²

Care and maintenance

For a long-term preservation of the properties of resin floors, we recommend a regular cleaning and care program. For further details see our FLOORFINDER Care and Maintenance Guide. Before first use we recommend performing basic cleaning and initial care.

Technical support

For system build up possibilities and detailed information relating to the laying of FLOORFINDER products, please refer to the FLOORFINDER System Planner or contact Floorfinder Asia Sdn. Bhd. directly.

Tel: +603 3290 7644

e-mail: info@floorfinderasia.com

Distributor:

Goodspeed America Inc., 24624 Interstate 45 North, Suite 200 • Spring, Texas 77386, U.S.A.,
email: bstorey@goodspeed-america.com | www.goodspeed-america.com

Manufacturer:

Floorfinder Asia Sdn. Bhd., No. 28, Lorong Sungai Puloh 1A/KU6, Jalan Sungai Puloh, Batu 5 3/4, Kapar, 42100 Klang, Selangor Darul Ehsan, Malaysia,
tel: +603 3290 7644, email: info@floorfinderasia.com, www.floorfinderasia.com – A division of VIACOR VISION AG, SWITZERLAND

Product 02452300 2-comp. PU top coating, soft elastic, low emission, colored

2 Application methods

Substrate preparation

The substrate must be clean and free of dust and loose particles. All traces of contaminants such as oils, fats, greases, paint residues, chemicals, algae and laitance should be removed. Depending on the desired evenness of the final coating FLOORFINDER PU-C523 is applied directly to the primer FLOORFINDER EP-P210 or to a FLOORFINDER PU-C523 based levelling layer. The coating FLOORFINDER PU-C523 must be applied not later than 24 hours after the application of the previous coat.

Primer

Apply an epoxy primer such as or FLOORFINDER EP-P210 by roller to the prepared surface. If the surface is porous, a second coat of primer may be necessary.

To improve inter-layer adhesion, sprinkle FLOORFINDER QS 0.3-0.6 mm quartz sand lightly (approx. 600 g/m²) while the primer is still wet. If two coats of primer are necessary, this should be done on the second coat.

Application

FLOORFINDER PU-C523 is supplied in 2-component containers in the right mixing ratio. The A-component must be stirred for at least 1–2 minutes. Then the entire content of the B component is emptied into the A-component container, and the two components are mixed until homogeneous using a suitable electric stirrer (for at least 2–3 minutes). The inclusion of air in the mixing process must be avoided. We recommend the application of equal numbers.

After mixing, transfer the material into a clean container and briefly stir again before application. Pour FLOORFINDER PU-C523 onto the prepared surface and spread evenly over the entire area using a suitable notched trowel. The recommended trowel sizes are:

No. 25 notched trowel (POLYPLAN): 1 mm
No. 48 notched trowel (POLYPLAN): 2 mm

The applied layer thickness should be checked during application to ensure the required coating thickness is achieved. While the coating is still liquid, we recommend rolling the surface with a metal spiked roller (e.g. Multi-tool) to ensure effective de-aeration and minimize the formation of air bubbles. The applicator should wear suitable spiked shoes during this operation, allowing

(C) Technical data

Mixed Product

1. Mixing ratio A:B	100: 20
2. Working time (25°C)	20 minutes
3. Application temperature:	10 – 30°C (min. 3K above dew point)
4. Material consumption Scratch coat/Levelling layer Coating	0.6 – 1.0 kg/m ² 2.8 – 3.0 kg/m ²
5. Foot traffic (20°C)	After 16-24 hours
6. Permissible RH %	50% - 80%
7. Re-coating interval	Within 24 hours
8. Fully cured properties: Mechanical (20°C) Chemical (20°C)	After 3 days After 7 days

Overcoating

It is not necessary to abrade the surface if the subsequent coat is applied within 24 hours. For application exceeded 24 hours or the coating has contact with dew or rainwater, please contact FLOORFINDER Technical Department for further detail.

3 Further information

CE-Mark



CE-Mark according to EN 13813

EN 13813: 2003-01, Screed material and floor screeds - Screed materials - Properties and requirements is the basis for requirements for floor screeds used in indoor flooring constructions. Resin coatings and sealer are also subject to this norm.
Details see CE-conformity mark and conformity declaration.

Distributor:

Goodspeed America Inc., 24624 Interstate 45 North, Suite 200 • Spring, Texas 77386, U.S.A.,
email: bstorey@goodspeed-america.com | www.goodspeed-america.com

Manufacturer:

Floorfinder Asia Sdn. Bhd., No. 28, Lorong Sungai Puloh 1A/KU6, Jalan Sungai Puloh, Batu 5 3/4, Kapar, 42100 Klang, Selangor Darul Ehsan, Malaysia,
tel: +603 3290 7644, email: info@floorfinderasia.com, www.floorfinderasia.com – A division of VIACOR VISION AG, SWITZERLAND

Product 02452300 2-comp. PU top coating, soft elastic, low emission, colored

movement across the freshly applied coating without damaging the surface.

Warnings and precautions

Information relating to the safe handling of this product can be found in the Material Safety Data Sheet. Local regulations concerning the safe handling of epoxy resin-based coating materials must be observed.

Suitable protective clothing including suitable eye protection must be worn.

Disclaimer

All information in this technical data sheet is based on our current knowledge and experience. This does not release the applicator from performing their own tests as many application factors, beyond our control, affect the application of our product. No guarantee of characteristics or suitability for a special purpose can be derived from this information. All present data, descriptions, drawings, photos, ratios, weights etc. are subject to change without prior notice and do not represent contracted characteristics of the product.

Due to different materials, sub-bases and working conditions, no guarantee of an application result or any liability claims can be derived from these details or from an unwritten technical advice except for liability claims based on:

-damage to life, body or health resulting from a negligent violation of obligations or a deliberate or negligent violation of obligation of a legal representative or assistant and if we are charged with intention or gross negligence.

The user has to test the products for their intended use. The user is responsible for following existing laws and orders and for observing third party trademark rights.

As all Floorfinder data sheets are updated on a regular basis it is the users responsibility to obtain the most recent issue (see www.floorfinderasia.com).

Distributor:

Goodspeed America Inc., 24624 Interstate 45 North, Suite 200 • Spring, Texas 77386, U.S.A.,
email: bstorey@goodspeed-america.com | www.goodspeed-america.com

Manufacturer:

Floorfinder Asia Sdn. Bhd., No. 28, Lorong Sungai Puloh 1A/KU6, Jalan Sungai Puloh, Batu 5 3/4, Kapar, 42100 Klang, Selangor Darul Ehsan, Malaysia,
tel: +603 3290 7644, email: info@floorfinderasia.com, www.floorfinderasia.com – A division of VIACOR VISION AG, SWITZERLAND